

## Washable, long-lasting, tacky booth coating with spectacular white finish

Like90 Tacky White is a water-based, low-VOC booth coating that traps overspray and other contamination on booth walls and doors, keeping it out of your paint work. It is fast and easy to apply and washes off easily with water. Now your booth can look like new in as little as one hour.



**IMPORTANT:** Recommended for paint booths that use heated air (i.e., a bake cycle) AND where the relative humidity in the booth does not exceed 85% continuously for extended periods of time. The coating will re-absorb moisture from the air and in some cases transfer to the touch. In extreme humidity, the coating may re-absorb enough moisture to run on vertical surfaces even several weeks after application. It will firm up again during a bake cycle or when booth humidity decreases. If the coating is applied when booth humidity is high, run a bake cycle immediately after application to help it firm up.

In non-bake booths, use only where booth humidity is controlled and does not exceed 70% RH. Test on a small section for 2 or 3 days to ensure the coating firms up and does not run.

Feature:	Benefits:
<i>White finish</i>	Eliminates the need to refinish booth surfaces covered with overspray. Restores booth to a like-new appearance. Optimizes lighting conditions for better paint work.
<i>Tacky coating</i>	Stays tacky for months, not weeks. Traps overspray, dirt and other contamination on booth surfaces, keeping it out of your paint work. Especially useful in areas with flying insects.
<i>Spray-on liquid</i>	Fast, easy application with conventional spray equipment already in use at the shop. Actual spray time for a typical booth is about 30 minutes.
<i>Water-soluble</i>	Fast, easy wash removal with water, even after months of extended use.
<i>Refreshable</i>	When coating begins to lose its tackiness, simply overcoat to refresh your booth. Coating should be removed completely and re-applied every 6 months.
<i>Water-based, low VOC</i>	Non-hazardous, environmentally friendly formula that is safe for disposal to municipal water facilities. (But check local regulations to determine if specific requirements exist.)

## Directions for Use

### Preparation:

1. Remove any temporary coating or protective film before applying. Make sure booth walls and other surfaces are completely dry. Freshly painted booth surfaces must be fully cured. *Optional:* For the best looking finish without repainting and to maximize coverage, nib existing rough overspray from walls with a 180 or 220 grit disc on a DA sander.
2. Mask any booth surfaces where coating is not needed or desired.
3. Turn on the booth's spray cycle and set booth temperature to 75° F (24° C).

### Application:

1. Shake or agitate coating in container.
2. Apply 1 medium wet coat (3 to 4 mils) to booth walls, doors, windows, and lights. Use a well-maintained HVLP gun with a 2.2mm tip and 20 psi at the gun. Your spray time for a typical booth should be less than 30 minutes. *Pressure Pot:* To best determine fluid volume, close down air pressure at gun and adjust pot pressure until stream shot from gun is 3 feet long. Set gun to 20 psi. *Airless:* 0.025 spray tip orifice with 90 degree fan.
3. Areas with heavy overspray may require a second coat for an even, white appearance.
4. Allow coating to cure so that it is no longer wet to touch. If booth humidity is high, run a bake cycle to help the coating firm up. Cured coating will be tacky to touch.
5. Use a damp sponge to remove any overspray.
6. Clean spray gun immediately with warm water.
7. To protect booth lights and windows, apply Like90 Tacky Clear booth coating in the same manner as described above for Tacky White.
8. NOTE: When coating begins to lose its tackiness, overcoat as desired by applying one or two wet coats. You should overcoat a maximum of 4 times. Coating should be completely removed and re-applied at least every 6 months.

### Removal:

1. Allow booth to cool to ambient temperature. TURN OFF ALL POWER TO BOOTH LAMPS.
2. Remove or protect filter gratings, if present to keep water out.
3. Using a hose or pressure washer, spray water onto all coated surfaces. Scrub heavy overspray areas with a wash mitt or brush. Rinse surfaces again.
4. Use compressed air to blow water away from all lights and glass surfaces.
5. Allow booth to dry. Remove water from floor with squeegee. When all surfaces are dry, re-apply coating.

### Packaging:

- 1-gallon bottle P/N 10043 (Ships in cases of four gallons)
- 5-gallon pail P/N 10044

### Technical Data:

- VOC content: 10 g/l calculated (less H<sub>2</sub>O and exempt compounds)
- Color: White liquid
- Coverage: About 535 square feet per gallon (theoretical) per 3 mil wet coat
- Flash point: >200°F (>93° C)
- Boiling point: 212°F (100° C)
- pH: 6 to 9
- Reactivity in water: none
- Specific gravity: 1.2

### IMPORTANT NOTICE TO PURCHASER:

The information in this document is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express and implied warranties (including the implied warranties of merchantability and fitness for a particular purpose): Except where prohibited by law, Seller's only obligation and your only remedy, is replacement or, at Seller's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will Seller be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

Distributed by: Bonding Solutions – 3703 West Parkway Blvd., West Valley City, UT 84120 USA - 888-954-5390 (888-9-LIKE90) - [www.like90.net](http://www.like90.net)