

Long-lasting, tacky booth coating with clear finish

Like90 Tacky Clear is a water-based, low-VOC booth coating that protects booth surfaces from paint overspray. In addition, it traps overspray and other contamination (e.g. insects) on booth walls, doors, windows and lights, keeping it out of your paint work. It is fast and easy to apply to all booth surfaces and washes off easily with water. Tacky Clear is ideal for new or recently repainted booths where the walls and doors are already white and provide good lighting conditions.



NOTE: The coating’s film absorbs moisture from the air and in extreme humidity, may transfer to the touch. In conditions where the relative humidity falls below 50% for an extended period of time, the coating may become less tacky. Tackiness can be restored by misting it lightly with water or by over-coating it with additional coating, as described below.

Feature:	Benefits:
<i>Clear finish</i>	Ideal for new or repainted booths that need reliable protection to stay looking new. Can also be applied to booth lights and windows. No need to mask any surfaces before applying.
<i>Tacky coating</i>	Traps overspray, dirt and other contamination on booth surfaces, keeping it out of your paint work. Especially useful in areas with flying insects. Stays tacky longer.
<i>Spray-on liquid</i>	Fast, easy application with conventional spray equipment already in use at the shop. Actual spray time for a typical booth is about 30 minutes.
<i>Water-soluble</i>	Fast, easy wash removal with water, even after months of extended use.
<i>Refreshable</i>	When coating begins to lose its tackiness, simply overcoat to refresh your booth. Coating should be removed completely and re-applied every 6 months.
<i>Water-based, low VOC</i>	Non-hazardous, environmentally friendly formula that is safe for disposal to municipal water facilities. (But check local regulations to determine if specific requirements exist.)

Directions for Use

Preparation:

1. Remove any temporary coating or protective film before applying. Make sure booth walls and other surfaces are completely dry. Freshly painted booth surfaces must be fully cured. *Optional:* For the best looking finish without repainting and to maximize coverage, nib existing rough overspray from walls with a 180 or 220 grit disc on a DA sander.
2. Mask any booth surfaces where Tacky Clear is not needed or desired.
3. Turn on the booth's spray cycle and set booth temperature to 75° F (24° C).

Application:

1. Shake or agitate coating in container.
2. Apply 1 medium wet coat (3 to 4 mils) to booth walls, doors, windows, and lights. Use a well-maintained HVLP gun with a 2.2mm tip and 20 psi at the gun. Your spray time for a typical booth should be less than 30 minutes. *Pressure Pot:* To best determine fluid volume, close down air pressure at gun and adjust pot pressure until stream shot from gun is 3 feet long. Set gun to 20 psi. *Airless:* 0.025 spray tip orifice with 90 degree fan.
3. Use a damp sponge to remove any overspray.
4. Clean spray gun immediately with warm water.
5. Allow coating to cure so that it is no longer wet to touch. Cured coating will be tacky to touch.
6. NOTE: When coating begins to lose its tackiness, overcoat as desired by applying one or two wet coats. You should overcoat a maximum of 4 times. Coating should be completely removed and re-applied at least every 6 months.

Removal:

1. Allow booth to cool to ambient temperature. TURN OFF ALL POWER TO BOOTH LAMPS.
2. Remove or protect filter gratings, if present to keep water out.
3. Using a hose or pressure washer, spray water onto all coated surfaces. Scrub heavy overspray areas with a wash mitt or brush. Rinse surfaces again.
4. Use compressed air to blow water away from all lights and glass surfaces.
5. Allow booth to dry. Remove water from floor with squeegee. When all surfaces are dry, re-apply coating.

Packaging:

- P/N 10045 Like90 Tacky Clear 1-gallon bottle (Ships in cases of four gallons)
- P/N 10046 Like90 Tacky Clear 5-gallon pail

Technical Data:

- VOC content: 10 g/l calculated (less H₂O and exempt compounds)
- Color: Slightly amber liquid
- Coverage: About 535 square feet per gallon (theoretical) per 3 mil wet coat
- Flash point: >200°F (>93° C)
- Boiling point: 212°F (100° C)
- pH: 6 to 9
- Reactivity in water: none
- Specific gravity: 1.1

IMPORTANT NOTICE TO PURCHASER:

The information in this document is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express and implied warranties (including the implied warranties of merchantability and fitness for a particular purpose): Except where prohibited by law, Seller's only obligation and your only remedy, is replacement or, at Seller's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will Seller be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.

Distributed by: Bonding Solutions – 3703 West Parkway Blvd., West Valley City, UT 84120 USA - 888-954-5390 (888-9-LIKE90) - www.like90.net